

**10%****PCW**  
AVAILABLE  
ON ALL PRODUCTS  
UPON REQUEST**PAPER SPECIFICATIONS****KRUGER COATED PAPER****KRUKOTE OFFSET**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
28#	70	85	42	1.61
30#	70	87	42	1.69
32#	70	87	45	1.77
34#	71	89	48	1.81
36#	71	89	50	1.93
38#	72	90	52	2.01
40#	72	91	55	2.13
45#	72	93	55	2.48
50#	72	95	55	2.83
60#	72	97	55	3.15

**KRUKOTE HI-BULK**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
32#	70	87	45	1.89

**KRUKOTE SATIN OFFSET**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
36#	72	92.7	35	2.32
38#	72	93.7	35	2.4
40#	70	94.2	35	2.52
45#	70	95.7	35	2.87
50#	70	97.1	35	3.07
60#	70	97	35	3.15

\*All values represent targets. Variations may occur during production.

**10%****PCW**AVAILABLE  
ON ALL PRODUCTS  
UPON REQUEST**PAPER SPECIFICATIONS****KRUGER COATED PAPER****KRUKOTE 76 OFFSET**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
32#	76	86	45	1.77
34#	76	88	48	1.81
36#	76	88	50	1.93
38#	76	89	52	2.01
40#	76	90	55	2.13
45#	76	92	55	2.48
50#	76	95	55	2.83
60#	76	97	55	3.15

**KRUKOTE 76 SATIN OFFSET**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
36#	76	92	35	2.32
38#	76	92.7	35	2.4
40#	76	93.3	35	2.52
45#	76	94.7	35	2.87
50#	76	95.7	35	3.07
60#	76	97	35	3.15

**KRUKOTE 80 OFFSET**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
36#	80	87	50	1.93
38#	80	88	52	2.01
40#	80	89	55	2.13
45#	80	91	55	2.48
50#	80	92	55	2.83
60#	80	94	55	3.15

**KRUKOTE 80 SATIN OFFSET**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
38#	80	92.5	35	2.4
40#	80	93	35	2.52
45#	80	94.5	35	2.87
50#	80	95.4	35	3.07
60#	80	96	35	3.39

\* All values represent targets. Variations may occur during production.

Publication  
Papers



**10%**

**PCW**  
AVAILABLE  
ON ALL PRODUCTS  
UPON REQUEST

**PAPER SPECIFICATIONS**

**KRUGER COATED PAPER**

**KRUKOTE PLUS OFFSET**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
40#	82	91.5	62	2.13
45#	82	92.2	65	2.48
50#	83	92.9	67	2.68
60#	84	93.6	68	2.95

**KRUKOTE PLUS SATIN OFFSET**

BASIS WEIGHT	BRIGHTNESS % (GE)	OPACITY % (TAPPI)	GLOSS %	CALIPER (MILS)
40#	82	91.5	35	2.13
45#	82	92.2	35	2.48
50#	83	92.9	35	2.68
60#	84	93.6	35	2.95

\*All values represent targets. Variations may occur during production.

AT KRUGER, WE DON'T JUST TALK INNOVATION...  
**WE PUT IT DOWN ON PAPER**

**KRUGER PUBLICATION PAPERS INC.**

3285 chemin Bedford  
Montréal, Québec, Canada H3S 1G5

Telephone: (514) 343-3100

**KRUGER PULP & PAPER SALES, INC.**

5 River Road, Suite 305  
Wilton, CT 06897-4069

Telephone: (203) 229-0333

[WWW.KRUGER.COM](http://WWW.KRUGER.COM)

